

Fiber OSP cable, TeraSPEED® Single Jacket All-Dielectric, 120 fiber, Gel-Free, Stranded Loose Tube, Singlemode G.652.D and G.657.A1, Feet jacket marking, Black jacket color


#### Product Classification

Regional Availability	Asia   Australia/New Zealand   EMEA   Latin America   North America
Portfolio	CommScope®
Product Type	Fiber OSP cable
Product Series	D-LN
General Specifications	
Cable Type	Stranded loose tube
Construction Type	Non-armored
Subunit Type	Gel-free
Jacket Color	Black
Jacket Marking	Feet
Subunit, quantity	10
Fibers per Subunit, quantity	12
Total Fiber Count	120
Dimensions	
Buffer Tube/Subunit Diameter	2.5 mm   0.098 in
Diameter Over Jacket	13.6 mm   0.535 in

### Representative Image

Page 1 of 7





#### Material Specifications

Jacket Material	PE
Mechanical Specifications	
Minimum Bend Radius, loaded	204 mm   8.032 in
Minimum Bend Radius, unloaded	136 mm   5.354 in
Tensile Load, long term, maximum	800 N   179.847 lbf
Tensile Load, short term, maximum	2700 N   606.984 lbf
Compression	22 N/mm   125.623 lb/in
Compression Test Method	FOTP-41   IEC 60794-1 E3
Flex	25 cycles
Flex Test Method	FOTP-104   IEC 60794-1 E6
Impact	4.41 N-m   39.032 in lb
Impact Test Method	FOTP-25   IEC 60794-1 E4
Strain	See long and short term tensile loads
Strain Test Method	FOTP-33   IEC 60794-1 E1
Twist	10 cycles
Twist Test Method	FOTP-85   IEC 60794-1 E7
Vertical Rise, maximum	694 m   2,276.903 ft
Optical Specifications	

Fiber Type

G.652.D and G.657.A1, TeraSPEED® | OS2

Page 2 of 7



#### **Environmental Specifications**

Installation temperature	-30 °C to +70 °C (-22 °F to +158 °F)
Operating Temperature	-40 °C to +70 °C (-40 °F to +158 °F)
Storage Temperature	-40 °C to +75 °C (-40 °F to +167 °F)
Cable Qualification Standards	ANSI/ICEA S-87-640   EN 187105
Environmental Space	Aerial, lashed   Buried
Jacket UV Resistance	UV stabilized
Water Penentration	24 h
Water Penentration Test Method	FOTP-82   IEC 60794-1 F5

#### **Environmental Test Specifications**

Cable Freeze Test Method F0TP-98   IEC 60794-1 F15   Heat Age -40 °C to +85 °C (-40 °F to +185 °F)   Heat Age Test Method IEC 60794-1 F9   Low High Bend -30 °C to +60 °C (-22 °F to +140 °F)   Kow High Bend Test Method F0TP-37   IEC 60794-1 E11   Temperature Cycle -40 °C to +70 °C (-40 °F to +158 °F)   Fomperature Cycle Test Method F0TP-31   IEC 60794-1 F1	Cable Freeze	-2 °C   28.4 °F
Heat Age Test Method IEC 60794-1 F9   Low High Bend -30 °C to +60 °C (-22 °F to +140 °F)   Low High Bend Test Method FOTP-37   IEC 60794-1 E11   Temperature Cycle -40 °C to +70 °C (-40 °F to +158 °F)	Cable Freeze Test Method	FOTP-98   IEC 60794-1 F15
Low High Bend -30 °C to +60 °C (-22 °F to +140 °F)   Low High Bend Test Method FOTP-37   IEC 60794-1 E11   Temperature Cycle -40 °C to +70 °C (-40 °F to +158 °F)	Heat Age	-40 °C to +85 °C (-40 °F to +185 °F)
Low High Bend Test Method   FOTP-37   I EC 60794-1 E11     Temperature Cycle   -40 °C to +70 °C (-40 °F to +158 °F)	Heat Age Test Method	IEC 60794-1 F9
Temperature Cycle   -40 °C to +70 °C (-40 °F to +158 °F)	Low High Bend	-30 °C to +60 °C (-22 °F to +140 °F)
	Low High Bend Test Method	FOTP-37   IEC 60794-1 E11
Temperature Cycle Test MethodFOTP-3   IEC 60794-1 F1	Temperature Cycle	-40 °C to +70 °C (-40 °F to +158 °F)
	Temperature Cycle Test Method	FOTP-3   IEC 60794-1 F1

#### Packaging and Weights

#### Cable weight

118 kg/km | 79.292 lb/kft

#### Regulatory Compliance/Certifications

Agency	Classification
CHINA-ROHS	Below maximum concentration value
ISO 9001:2015	Designed, manufactured and/or distributed under this quality management system
REACH-SVHC	Compliant as per SVHC revision on www.commscope.com/ProductCompliance
ROHS	Compliant
UK-ROHS	Compliant



#### Included Products

CS-8W-LT

Page 3 of 7



----

- TeraSPEED® G652D/G657A1 Singlemode Fiber

### \* Footnotes

**Operating Temperature** Specification applicable to non-terminated bulk fiber cable

Page 4 of 7



#### TeraSPEED® G652D/G657A1 Singlemode Fiber

# TeraSPEED®

#### Product Classification

Portfolio	CommScope®
Product Type	Optical fiber
General Specifications	
Cladding Diameter	125 µm
Cladding Diameter Tolerance	±0.7 µm
Cladding Non-Circularity, maximum	0.7 %
Coating Diameter (Colored)	249 µm
Coating Diameter (Uncolored)	242 µm
Coating Diameter Tolerance (Colored)	±13 µm
Coating Diameter Tolerance (Uncolored)	±5 μm
Coating/Cladding Concentricity Error, maximum	12 µm
Core Diameter	8.3 µm
Core/Clad Offset, maximum	0.5 µm
Proof Test	689.476 N/mm²   100000 psi
Dimensions	
Fiber Curl, minimum	4 m   13.123 ft
Mechanical Specifications	
Macrobending, 20 mm Ø mandrel, 1 turn	0.75 dB @ 1,550 nm   1.50 dB @ 1,625 nm
Macrobending, 30 mm Ø mandrel, 10 turns	0.25 dB @ 1,550 nm   1.00 dB @ 1,625 nm
Macrobending, 60 mm Ø mandrel, 100 turns	0.05 dB @ 1,550 nm   0.05 dB @ 1,625 nm
Coating Strip Force, maximum	8.9 N   2.001 lbf

Page 5 of 7



# <u>CS-8W-L</u>T

Coating Strip Force, minimum	1.3 N   0.292 lbf
Dynamic Fatigue Parameter, minimum	20
Optical Specifications	
Cabled Cutoff Wavelength, maximum	1260 nm
Point Defects, maximum	0.1 dB
Zero Dispersion Slope, maximum	0.092 ps/[km-nm-nm]
Zero Dispersion Wavelength, maximum	1324 nm
Zero Dispersion Wavelength, minimum	1300 nm
Optical Specifications, Wavelength Specific	
Attenuation, maximum	0.22 dB/km @ 1,550 nm   0.25 dB/km @ 1,490 nm   0.25 dB/km @ 1,625 nm   0.36 dB/km @ 1,310 nm   0.36 dB/km @ 1,385 nm
Attenuation, typical	0.19 dB/km @ 1,550 nm   0.33 dB/km @ 1,310 nm
Backscatter Coefficient	-79.6 dB @ 1,310 nm   -82.1 dB @ 1,550 nm
Dispersion, maximum	18 ps(nm-km) at 1550 nm ( 3.5 ps(nm-km) from 1285 nm to 1330 nm at 1310 nm
Index of Refraction	1.467 @ 1,310 nm   1.467 @ 1,385 nm   1.468 @ 1,550 nm
Mode Field Diameter	10.4 μm @ 1,550 nm   9.2 μm @ 1,310 nm   9.6 μm @ 1,385 nm
Mode Field Diameter Tolerance	±0.4 μm @ 1310 nm   ±0.5 μm @ 1550 nm   ±0.6 μm @ 1385 nm
Polarization Mode Dispersion Link Design Value, maximum	0.04 ps/sqrt(km)
Standards Compliance	IEC 60793-2-10, edition 6, model A1a.4   ITU-T G.652. D   ITU-T G.657.A1   TIA-492CAAB (OS2)
Environmental Specifications	
Host Aging maximum	$0.05 dP/km \otimes 95 °C$

Heat Aging, maximum	0.05 dB/km @ 85 °C
Temperature Dependence, maximum	0.05 dB/km
Temperature Humidity Cycling, maximum	0.05 dB/km
Water Immersion, maximum	0.05 dB/km @ 23 °C

#### Regulatory Compliance/Certifications

Agency

Classification

Page 6 of 7



### CS-8W-LT

ISO 9001:2015

Designed, manufactured and/or distributed under this quality management system

#### \* Footnotes

Temperature Dependence, maximum	Temperature dependence is conducted at -60 °C to +85 °C (-76 °F to +185 °F)
Temperature Humidity Cycling, maximum	Temperature humidity cycling is conducted at -10 °C to +85 °C (+14 °F to +185 °F) up to 95% relative humidity

