CX3750009 | 200T040P3625JCASS COEX

ConQuest® Cable in Conduit, 2 in, SCH 40, terracotta (P3® 625 JCASS)



 *Product complies with the Build America, Buy America Act (BABAA) requirements of the Infrastructure Investment and Jobs Act of 2021 (Pub. L. 117- 58, §§ 70901-70953), or is the subject of a waiver approved by the Secretary of Commerce or designee. Compliance requirements and waiver applicability vary based on government funding program. Check the laws and regulations for your specific program.

Product Classification

Regional Availability North America

Product Type Coaxial cable-in-conduit

Product Brand ConQuest®
Product Series 625 Series

Government FundingBuild America Buy America (BABA) compliant*

General Specifications

Cable Type625 SeriesCable-In-Conduit TypeP3® in ductColorTerracottaConduit TypeNon-toneableWall TypeSmooth

Dimensions

Length 731.52 m | 2400 ft

Wall Thickness Designation SCH 40
Nominal Size 2 in

Packaging and Weights

Weight, net 918.197 kg/km | 617 lb/kft

Included Products

530101403 - 75 Ohm P3® Trunk and Distribution Cable, black PE jacket, flooded for underground P3® 625 JCASS SM MT

COMMSCOPE®

CX3750009 | 200T040P3625JCASS COEX

5308103 P3® 625 JCASS 75 Ohm P3® Trunk and Distribution Cable, black PE jacket, flooded for underground

CX3799999 200T040 EMPTY DUCT COEX ConQuest® Empty Conduit, 2 in, SCH 40, terracotta



530101403 | P3® 625 JCASS SM MT

75 Ohm P3® Trunk and Distribution Cable, black PE jacket, flooded for underground



Product Classification

Product Type Coaxial hardline cable

Product Brand P3®

Warranty One year

General Specifications

Cable Type625 SeriesConstruction TypeSwagedJacket ColorBlack

Dimensions

Cable Length 731.52 m | 2400 ft **Diameter Over Center Conductor, nominal** 3.48 mm | 0.137 in **Diameter Over Dielectric, nominal** 14.351 mm | 0.565 in **Diameter Over Inner Jacket, nominal** 17.653 mm | 0.695 in **Diameter Over Jacket, nominal** 21.59 mm | 0.85 in **Diameter Over Outer Conductor, nominal** 15.875 mm | 0.625 in Armor Thickness, nominal 0.203 mm | 0.008 in 0.762 mm | 0.03 in Inner Jacket Thickness, nominal 0.762 mm | 0.03 in Jacket Thickness, nominal **Outer Conductor Thickness, nominal** 0.762 mm | 0.03 in

Electrical Specifications

Capacitance 50.197 pF/m | 15.3 pF/ft

Capacitance Tolerance ±1.0 pF/ft

COMMSCOPE®

530101403 | P3® 625 JCASS SM MT

Characteristic Impedance75 ohmCharacteristic Impedance Tolerance±2 ohm

dc Resistance Note Nominal values based on a standard condition of 20 °C (68 °F)

dc Resistance, Inner Conductor, nominal2.756 ohms/km | 0.84 ohms/kftdc Resistance, Loop, nominal3.609 ohms/km | 1.1 ohms/kftdc Resistance, Outer Conductor, nominal0.853 ohms/km | 0.26 ohms/kft

Jacket Spark Test Voltage5000 VacNominal Velocity of Propagation (NVP)87 %

Operating Frequency Band 5-3000 MHz

Structural Return Loss 24 dB @ 1003-1218 MHz | 24 dB @ 1219-1794 MHz | 30 dB @ 5-1002

MHz

Structural Return Loss, Grade N ≥24 dB @ 1003−1218 MHz | ≥24 dB @ 1219−1794 MHz | ≥30 dB @ 5−1002

MHz

Attenuation

Frequency (MHz)	Attenuation (dB/100 m)	Attenuation (dB/100 ft)
5.0	0.43	0.13
55.0	1.48	0.45
85.0	1.84	0.56
204.0	2.92	0.89
211.0	3.02	0.92
250.0	3.28	1
300.0	3.54	1.08
350.0	3.87	1.18
400.0	4.17	1.27
450.0	4.43	1.35
500.0	4.69	1.43
550.0	4.92	1.5
600.0	5.18	1.58
750.0	5.84	1.78
865.0	6.33	1.93
1002.0	6.92	2.11
1218.0	7.62	2.32
1500.0	8.74	2.66
1794.0	9.7	2.96

Page 4 of 10



530101403 | P3® 625 JCASS SM MT

1800.0	9.72	2.96
2000.0	10.34	3.15
2200.0	10.95	3.34
2500.0	11.81	3.6
2700.0	12.37	3.77
3000.0	13.19	4.02

Material Specifications

Center Conductor Material Copper-clad aluminum

Dielectric Material Foam PE

Jacket Material PE

Outer Conductor Material Aluminum

Mechanical Specifications

Minimum Bend Radius, bonded114.3 mm4.5 inPulling Tension, maximum215.456 kg475 lb

Environmental Specifications

Corrosion Protection Migraheal®

Environmental Space Buried

Packaging and Weights

Packaging Type Reel

Weight, gross 278.287 kg/km | 187 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system





5308103 | P3® 625 JCASS

75 Ohm P3® Trunk and Distribution Cable, black PE jacket, flooded for underground



 *Product complies with the Build America, Buy America Act (BABAA) requirements of the Infrastructure Investment and Jobs Act of 2021 (Pub. L. 117- 58, §§ 70901-70953), or is the subject of a waiver approved by the Secretary of Commerce or designee. Compliance requirements and waiver applicability vary based on government funding program. Check the laws and regulations for your specific program.

Product Classification

Regional Availability North America

Product Type Coaxial hardline cable

Product Brand P3®

Government FundingBuild America Buy America (BABA) compliant*

Warranty One year

General Specifications

Cable Type625 SeriesConstruction TypeSwagedJacket ColorBlack

Short Description P3 625 JCASS SM PR997

Dimensions

Cable Length 731.52 m | 2400 ft **Diameter Over Center Conductor, nominal** 3.48 mm | 0.137 in **Diameter Over Dielectric, nominal** 14.351 mm | 0.565 in **Diameter Over Inner Jacket, nominal** 17.653 mm | 0.695 in **Diameter Over Jacket, nominal** 21.59 mm | 0.85 in **Diameter Over Outer Conductor, nominal** 15.875 mm | 0.625 in Armor Thickness, nominal 0.203 mm | 0.008 in Inner Jacket Thickness, nominal 0.762 mm | 0.03 in Jacket Thickness, nominal 0.762 mm | 0.03 in **Outer Conductor Thickness, nominal** 0.762 mm | 0.03 in





5308103 | P3® 625 JCASS

Electrical Specifications

Capacitance 50.197 pF/m | 15.3 pF/ft

Capacitance Tolerance $\pm 1.0 \text{ pF/ft}$ Characteristic Impedance75 ohmCharacteristic Impedance Tolerance $\pm 2 \text{ ohm}$

dc Resistance Note Nominal values based on a standard condition of 20 °C (68 °F)

dc Resistance, Inner Conductor, nominal2.756 ohms/km | 0.84 ohms/kftdc Resistance, Loop, nominal3.609 ohms/km | 1.1 ohms/kftdc Resistance, Outer Conductor, nominal0.853 ohms/km | 0.26 ohms/kft

Jacket Spark Test Voltage5000 VacNominal Velocity of Propagation (NVP)87 %

Operating Frequency Band 5-3000 MHz

Structural Return Loss 24 dB @ 1003-1218 MHz | 24 dB @ 1219-1794 MHz | 30 dB @ 5-1002

ИHz

Structural Return Loss, Grade N ≥24 dB @ 1003−1218 MHz | ≥24 dB @ 1219−1794 MHz | ≥30 dB @ 5−1002

MHz

Attenuation

Frequency (MHz)	Attenuation (dB/100 m)	Attenuation (dB/100 ft)
5.0	0.43	0.13
55.0	1.48	0.45
85.0	1.84	0.56
204.0	2.92	0.89
211.0	3.02	0.92
250.0	3.28	1
300.0	3.54	1.08
350.0	3.87	1.18
400.0	4.17	1.27
450.0	4.43	1.35
500.0	4.69	1.43
550.0	4.92	1.5
600.0	5.18	1.58
750.0	5.84	1.78
865.0	6.33	1.93



5308103 | P3® 625 JCASS

6.92	2.11
7.62	2.32
8.74	2.66
9.7	2.96
9.72	2.96
10.34	3.15
10.95	3.34
11.81	3.6
12.37	3.77
13.19	4.02
	7.62 8.74 9.7 9.72 10.34 10.95 11.81 12.37

Material Specifications

Center Conductor Material Copper-clad aluminum

Dielectric Material Foam PE

Jacket Material PE

Outer Conductor Material Aluminum

Mechanical Specifications

Minimum Bend Radius, bonded114.3 mm4.5 inPulling Tension, maximum215.456 kg475 lb

Environmental Specifications

Corrosion Protection Migraheal®

Environmental Space Buried

Packaging and Weights

Packaging Type Reel

Weight, gross 278.287 kg/km | 187 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system





CX3799999 | 200T040 EMPTY DUCT COEX



ConQuest® Empty Conduit, 2 in, SCH 40, terracotta

Product Classification

Product TypeEmpty conduitProduct BrandConQuest®

General Specifications

ColorTerracottaConduit TypeNon-toneableDensity Test MethodASTM D792A

 Density, maximum
 0.955 g/cm³ | 0.035 lb/in³

 Density, minimum
 0.941 g/cm³ | 0.034 lb/in³

Design Standard ASTM D3350-05

Wall Type Smooth

Dimensions

Length 762 m | 2500 ft

 Inner Diameter, nominal
 51.994 mm | 2.047 in

 Outer Diameter, nominal
 60.325 mm | 2.375 in

Wall Thickness Designation SCH 40

Wall Thickness, minimum 3.912 mm | 0.154 in

Nominal Size 2 in

Material Specifications

Flexural Modulus, minimum 551.581 N/mm² | 80000 psi

Flexural Property Test Method ASTM D790

Hydrostatic Design BasisNot pressure rated

Hydrostatic Design Test MethodASTM D2837

Material Type High density polyethylene (HDPE)

Melt Flow Rate Test Method ASTM D1238

COMMSCOPE®

CX3799999 | 200T040 EMPTY DUCT COEX

Melt Flow Rate, maximum 0.39 g/10 min

Mechanical Specifications

Minimum Bend Radius, unsupported 660.4 mm | 26 in

Tensile Property Test Method ASTM D638

Tensile Strength at yield, minimum $20.684 \text{ N/mm}^2 \mid 3000 \text{ psi}$ Pulling Tension, maximum $1,043.262 \text{ kg} \mid 2300 \text{ lb}$

Environmental Specifications

Environmental Stress Crack Resistance Failure rate of 10% within 96 hours

Environmental Stress Test Method ASTM D1693, ESCR Condition B

Packaging and Weights

Weight, net 702.413 kg/km | 472 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system



* Footnotes

Environmental Stress Crack Resistance ESCR—Environmental Stress Crack Resistence

